

# Sylvin 5153-89 White 1399

Polyvinyl Chloride  
Sylvin Technologies Incorporated

Message:  
Sylvin 5153-89 White 1399 Is A Non Lead Stabilized Vinyl Compound Formulated For Wire Insulation Applications.

General Information			
Uses	Wire and cable applications		
	Insulating material		
Appearance	White		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A	89		ASTM D2240
Shaw A, 10 seconds	89		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	15.2	MPa	ASTM D638
Tensile Elongation (Break)	300	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength	70.1	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	105	°C	ASTM D794
Melting Temperature	171 - 182	°C	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	26	%	ASTM D2863

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT