

KOPELEN J-340C

Polypropylene Impact Copolymer

Lotte Chemical Corporation

Message:

J-340C is impact block copolymer with ethylene content as co-monomer.
This grade is designed to be processed in conventional Injection molding equipment.
J-340C shows good impact resistance at low temperature and has also high stiffness.
It has broad range of property, and is used from industrial supplies to cap & closure base resin.

General Information			
Features	Block Copolymer		
	Good Impact Resistance		
	High Stiffness		
	Low Temperature Impact Resistance		
Uses	Caps		
	Closures		
	Containers		
	Toys		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	27.5	MPa	ASTM D638
Tensile Elongation (Break)	> 100	%	ASTM D638
Flexural Modulus	1370	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-10°C	29	J/m	
23°C	78	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	120	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

