

TOLEN H020 GP

Polypropylene Homopolymer
SIBUR, LLC

Message:

PP H020 GP is a polypropylene homopolymer with standard molecular mass distribution. The product features fluidity below average, an optimal stabilization package and balanced physical and mechanical properties.

General Information	
Features	General Purpose
	Good Stability
	Homopolymer
	Low Flow
	Narrow Molecular Weight Distribution

Uses	General Purpose
Processing Method	Extrusion
	Injection Molding
	Thermoforming

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Yield)	30.0	MPa	Internal Method
Tensile Strain ² (Yield)	10	%	Internal Method
Flexural Modulus ³	1500	MPa	Internal Method
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	2.0	kJ/m ²	Internal Method
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	80.0	°C	Internal Method
Vicat Softening Temperature	155	°C	Internal Method ⁴

NOTE	
1.	50 mm/min
2.	50 mm/min
3.	5.0 mm/min
4.	A (10N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

