

REV Materials 8008-002

Polypropylene
REV Materials

Message:

20% wollastonite dispersed in a polypropylene matrix suitable for injection molding applications.

General Information			
Filler / Reinforcement	Wollastonite (CaSiO3), 20% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3030	MPa	ASTM D638
Tensile Strength	29.0	MPa	ASTM D638
Tensile Elongation (Break)	3.9	%	ASTM D638
Flexural Modulus	2620	MPa	ASTM D790
Flexural Strength	54.5	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	19	J/m	ASTM D256
Unnotched Izod Impact	250	J/m	ASTM D256
Injection	Nominal Value	Unit	
Rear Temperature	149 - 232	°C	
Middle Temperature	149 - 232	°C	
Front Temperature	149 - 232	°C	
Nozzle Temperature	149 - 232	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT