

# Badaprene® TPV 55A 1049

Polypropylene + EPDM Rubber

Bada AG

## Message:

Suitable for automotive interior with low smell and low emissions, "transparent", very easy to be colored

General Information			
Features	Good Colorability		
	Low Odor Transfer		
	Low to No Odor		
Uses	Automotive Applications		
Appearance	Clear/Transparent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm <sup>3</sup>	DIN 53505
Elastomers	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	55		DIN 53505
Tensile Stress - Flow (Yield)	4.10	MPa	DIN 53505
Tensile Elongation - Flow (Break)	500	%	DIN 53505
Tear Strength - Flow	20	kN/m	DIN 53505
Compression Set (70°C, 24 hr)	37	%	DIN 53505

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT