Wanthane® WHT-1185

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

Message:

WHT-1185 is polyester-based TPU for injection molding and extrusion applications, supplied in form of transparent, translucent, colorless or slightly yellowish pellets with the characteristic of Plasticizer Free, Excellent strength, resilience and abrasion resistance

Applications:

Shoes, Compounding, Belt etc

General Information

General Information			
Features	Good Abrasion Resistance		
	Good Strength		
	Resilient		
Uses	Belts/Belt Repair		
	Compounding		
	Footwear		
Appearance	Colorless		
	Translucent		
	Transparent - Slight Yellow		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	6.00	MPa	
300% Strain	12.0	MPa	
Tensile Strength	33.0	MPa	ASTM D412
Tensile Elongation (Break)	520	%	ASTM D412
Tear Strength	100	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-35.0	°C	ASTM D3417
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	

Drying Time	2.0 to 3.0	hr
Rear Temperature	190	°C
Middle Temperature	195	°C
Front Temperature	200	°C
Nozzle Temperature	205	°C
Injection Pressure	70.0	MPa
Fishmatica	Name in al Value	11
Extrusion	Nominal Value	Unit
Drying Temperature	90.0 to 100	°C
Drying Temperature	90.0 to 100	°C
Drying Temperature Drying Time	90.0 to 100 3.0 to 4.0	°C hr
Drying Temperature Drying Time Cylinder Zone 1 Temp.	90.0 to 100 3.0 to 4.0 190	°C hr °C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

