

LNP™ LUBRILOY™ UX98388 compound

Polyphthalamide

SABIC Innovative Plastics

Message:

LNP LUBRILOY* UX98388 is a compound based on Polyphthalamide resin containing Proprietary Lubricant. Added feature of this material is: Wear Resistant.

Also known as: LNP* LUBRILOY* Compound PDX-U-98388

Product reorder name: UX98388

General Information			
Additive	Lubricant		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Molding Shrinkage			
Flow	2.5	%	Internal Method
Across Flow : 24 hr	1.6	%	ISO 294-4
Flow : 24 hr	1.6	%	ISO 294-4
Water Absorption (23°C, 24 hr)	0.34	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2600	MPa	ISO 527-2/1
Tensile Stress			
Yield	72.0	MPa	ISO 527-2
Yield	78.0	MPa	ISO 527-2/5
Break	67.0	MPa	ISO 527-2/5
Tensile Strain (Yield)	6.1	%	ISO 527-2/5
Flexural Modulus			ISO 178
--	2500	MPa	
-- ¹	2400	MPa	
Flexural Stress	106	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	14	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ³ (0.45 MPa, Unannealed, 64.0 mm Span)	131	°C	ISO 75-2/Bf
CLTE - Transverse (23 to 60°C)	9.1E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	

Drying Time	4.0	hr
Suggested Max Moisture	0.15	%
Rear Temperature	310 to 321	°C
Middle Temperature	316 to 327	°C
Front Temperature	327 to 338	°C
Processing (Melt) Temp	316 to 332	°C
Mold Temperature	149 to 171	°C
Back Pressure	0.172 to 0.344	MPa
Screw Speed	30 to 60	rpm

NOTE

1. 2.0 mm/min
2. 80*10*4
3. 80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

