

# ENVIROLOY® ENV15-NC530

Polycarbonate + ABS

ENVIROPLAS®, Inc.

## Message:

Injection Molding Grade, 10% Fiberglass Reinforced, RoHS Compliant  
NC530 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color.  
The ENV15 Series Products Are Available With Mold Release and/or UV Stabilizer.  
Contact Enviroplas Regarding UL Recognized Versions Of This Product.

General Information			
Filler / Reinforcement	Glass Fiber, 10% Filler by Weight		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.60	%	ASTM D955
Ash Content	10	%	ASTM D5630
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	62.1	MPa	ASTM D638
Flexural Modulus	3920	MPa	ASTM D790
Flexural Strength	107	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	124	°C	
1.8 MPa, Unannealed	113	°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	238 to 260	°C	
Middle Temperature	243 to 271	°C	

Front Temperature	249 to 277	°C
Nozzle Temperature	243 to 271	°C
Mold Temperature	76.7 to 98.9	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.345 to 0.689	MPa
Screw Speed	40 to 70	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

