

Sumiliteresin® PR-NVK 83 I

Phenolic

SBHPP

Message:

SUMILITERESIN® PR-NVK 83 I is Liquid resol phenolic resin with melamine modified. It is generally applied for clutch facing.

Characteristics

SUMILITERESIN® PR-NVK 83 I is liquid melamine modified phenolic resin and this is solvent base. By using this kind of resin, friction properties will much improve such as judder and hardness.

General Information		
Appearance	Red	
Forms	Liquid	
Additional Information	Nominal Value	Unit
Resin Content (135°C)	39 - 45	%
Uncured Properties	Nominal Value	Unit
Density (25°C)	0.998 - 1.04	g/cm ³
Viscosity (25°C)	5.0E-3 - 0.025	Pa·s
Gel Time (165°C)	0.75 - 1.3	min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

