## Hyundai EP PA66 LD170

## Polyamide 66

HYUNDAI EP Co., Ltd.

## Message:

Hyundai EP PA66 LD170 is a Polyamide 66 (Nylon 66) product filled with 35% glass fiber. It is available in Asia Pacific. Primary characteristic: heat stabilizer.

| General Information  |                                  |         |             |
|--|----------------------------------|---------|-------------|
| Filler / Reinforcement                                     | Glass Fiber,35% Filler by Weight |         |             |
| Additive   | Heat Stabilizer                  |         |             |
| Features   | General Purpose                  |         |             |
|  | Heat Stabilized                  |         |             |
| Uses   | General Purpose                  |         |             |
| Forms  | Pellets                          |         |             |
| Physical   | Nominal Value                    | Unit    | Test Method |
| Density  | 1.38                             | g/cm³   | ASTM D1505  |
| Molding Shrinkage - Flow                                   | 0.30 to 0.60                     | %       | ASTM D955   |
| Ash Content  | 35                               | %       |             |
| Hardness   | Nominal Value                    | Unit    | Test Method |
| Rockwell Hardness (R-Scale)                                | 121                              |         | ASTM D785   |
| Mechanical   | Nominal Value                    | Unit    | Test Method |
| Tensile Strength (Yield)                                   | 147                              | MPa     | ASTM D638   |
| Flexural Modulus   | 6370                             | MPa     | ASTM D790   |
| Flexural Strength  | 196                              | MPa     | ASTM D790   |
| Impact   | Nominal Value                    | Unit    | Test Method |
| Notched Izod Impact (23°C)                                 | 9.8                              | J/m     | ASTM D256   |
| Thermal  | Nominal Value                    | Unit    | Test Method |
| Deflection Temperature Under Load (1.8<br>MPa, Unannealed) | 250                              | °C      | ASTM D648   |
| Melting Temperature  | 265                              | °C      |             |
| Electrical   | Nominal Value                    | Unit    | Test Method |
| Volume Resistivity   | 1.0E+13 to 1.0E+15               | ohms·cm | ASTM D257   |
| Dielectric Strength  | 3.5                              | kV/mm   | ASTM D149   |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

