

Spartech Polycom SC7A21-2800

Polycarbonate + PBT

Spartech Polycom

Message:

Spartech SC7A21-2800 is an impact modified, PC/PBT alloy for injection molding applications.

The alloys bridge desirable characteristics of both resins. They benefit from the flow characteristics of PBT, and the high heat distortion temperature is influenced by the polycarbonate fraction. The alloys approach the toughness of polycarbonate without the thickness sensitivity.

A very versatile product for a wide variety of applications, Spartech SC7A21-2800 is recommended for industrial, transportation, sporting goods and electrical/electronic applications.

General Information			
Additive	Impact modifier		
Features	Impact modification		
	Impact resistance, good		
	Good liquidity		
	Heat resistance, high		
	Good toughness		
Uses	Electrical/Electronic Applications		
	Industrial application		
	Application in Automobile Field		
	Sporting goods		
Appearance	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR)	8.0	g/10 min	ASTM D1238
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	350	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	87.8	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	249 - 282	°C	
Middle Temperature	254 - 288	°C	
Front Temperature	260 - 293	°C	
Nozzle Temperature	274 - 302	°C	
Processing (Melt) Temp	274 - 302	°C	
Mold Temperature	82.2 - 93.3	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

