

POCAN® B 3233 HR 000000

Polybutylene Terephthalate

LANXESS GmbH

Message:

PBT, 30 % glass fibers, injection molding, improved flowability, hydrolysis stabilized

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	Hydrolysis resistance		
Features	Good liquidity		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.48	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/2.16 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction: 260°C, 2.00mm ¹	1.0	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.10	%	ISO 294-4
Flow direction: 260°C, 2.00mm ³	0.30	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.10	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9600	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	125	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.9	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	9100	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	200	MPa	ISO 178
Flexural Strain at Flexural Strength ⁷ (23°C)	3.2	%	
Burning Behavior ⁸	passed		ISO 3795
ISO Shortname	PBT, GHMRW, 09-100, GF30		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	55	kJ/m ²	ISO 179/1eU
23°C	65	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A

23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	55	kJ/m ²	ISO 180/1U
23°C	55	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	205	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B120
Melting Temperature ⁹	225	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	3.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.3E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	450	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	HB		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.800 mm	800	°C	IEC 60695-2-12
1.50 mm	800	°C	IEC 60695-2-12
3.00 mm	800	°C	IEC 60695-2-12
Glow Wire Ignition Temperature			IEC 60695-2-13
0.800 mm	825	°C	IEC 60695-2-13
1.50 mm	825	°C	IEC 60695-2-13
3.00 mm	825	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
Processing (Melt) Temp	250 - 270	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	60x60x2; MT 80°C; 600 Bar		
2.	60x60x2		
3.	60x60x2; MT 80°C; 600 Bar		
4.	60x60x2		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	Pull Rate: 2 mm/min; 50% RH		
8.	US-FMVSS302		
9.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

