

ESTADIENE 2525 AS

Acrylonitrile Butadiene Styrene

Cossa Polimeri S.r.l.

Message:

ESTADIENE 2525 AS is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Europe. Applications of ESTADIENE 2525 AS include appliances and engineering/industrial parts.

Characteristics include:

- Flame Rated
- Antistatic
- Good Processability
- Impact Resistant

General Information			
Additive	Antistatic		
Features	Antistatic		
	Good Flow		
	Good Processability		
	High Impact Resistance		
Uses	Appliances		
	Engineering Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	37.0	MPa	
Break	31.0	MPa	
Tensile Elongation (Break)	20	%	ASTM D638
Flexural Modulus	2500	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°C	200	J/m	
23°C	250	J/m	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	101	°C	ASTM D1525 ¹
--	93.0	°C	ASTM D1525 ²

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	HB		
3.20 mm	HB		
Glow Wire Ignition Temperature (2.00 mm)	650	°C	IEC 60695-2-13


NOTE			
1.	Rate A (50°C/h), Loading 1 (10 N)		
2.	Rate A (50°C/h), Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT