

SABIC® PPcompound 8611P

Polypropylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® PPcompound 8611P is a development grade, elastomer-modified mineral filled Polypropylene for automotive exterior applications. This material has been designed to combine a good stiffness and excellent impact performance with good processing and surface esthetics. This grade is UV stabilised and is suitable for painted applications also.

SABIC® PPcompound 8611P is a designated automotive grade.

General Information			
Filler / Reinforcement	Mineral filler		
Additive	Impact modifier		
	UV stabilizer		
Features	Impact modification		
	Rigid, good		
	Impact resistance, high		
	Good UV resistance		
	Workability, good		
	Sprayable		
Uses	Application in Automobile Field		
	Automotive exterior parts		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.985	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	37	g/10 min	ISO 1133
Molding Shrinkage (24 hr)	0.70 - 0.80	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, Injection Molded)	20.0	MPa	ISO 527-2/1A
Tensile Strain (Break, Injection Molded)	80	%	ISO 527-2/1A
Flexural Modulus ¹ (Injection Molded)	1650	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-20°C, injection molding	10	kJ/m ²	ISO 180/1A
0°C, injection molding	30	kJ/m ²	ISO 180/1A
23°C, injection molding	40	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (1.8 MPa, Unannealed)	53.0	°C	ISO 75-2/A
---	------	----	------------

NOTE

1. Type 1A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

