

CoREZYN® COR30-DA-250

Thermoset Polyester
Interplastic Corporation

Message:

CoREZYN also supplies isophthalic and orthophthalic polyester resins for applications used in less severe environments. End-use applications include beams, pipes, channels, tubing and more.

General Information	
Features	Isophthalic
	Low Viscosity
	Medium Reactivity
	Resilient

Uses	Piping
	Tubing

Additional Information	Nominal Value	Unit
Gel to Peak	1.0 to 3.0	min
Non-Volatile Content	65 to 70	%
Peak Exotherm	199 to 227	°C

Uncured Properties	Nominal Value	Unit
Viscosity (25°C, Brookfield HBT)	0.70 to 1.2	Pa·s
Gel Time ¹	4.0 to 6.0	min

NOTE	
1.	SPI gel time run in 180°F (82°C) water bath, catalyzed with 1.0 phr of 98% benzyol peroxide, minutes.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT