Geon[™] Vinyl Wire & Cable WJMS800

Flexible Polyvinyl Chloride

PolyOne Corporation

Message:

Geon[™]Vinyl Wire & Cable WJMS800 is a flexible PVC product. It can be processed by extrusion coating and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: wire and cable. Features include: ROHS certification Flame Retardant

General Information				
Features	Flame retardancy			
Uses	Wire and cable applications			
	High voltage insulation			
	Insulating material			
Wire Types	AWM			
	FT-4			
RoHS Compliance	RoHS compliance			
Forms	Particle			
Processing Method	Extrusion coating			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	1.39	g/cm³	ASTM D792	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D, 15 sec)	41		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength ¹ (Yield)	18.6	MPa	ASTM D638	
Tensile Elongation ² (Break)	300	%	ASTM D638	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	-29.0	°C	ASTM D746	
UL Temperature Rating	105	°C		
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	6.0E+13	ohms·cm	ASTM D257	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index (3.18 mm)	31	%	ASTM D2863	
Additional Information				
NOTE: Typical Properties of Molded Slab (0.075"); Not to be Construed as Speci	fications.		
Extrusion	Nominal Value	Unit		
Melt Temperature	166 - 182	°C		
NOTE				

1.	Type 4, 510mm/min
2.	Type 4, 510mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

