

# LUVOCOM® 1100-7721/WT9016

Polyethersulfone  
Lehmann & Voss & Co.

Message:

LUVOCOM® 1100-7721/WT9016 is a polyethersulfone (PES) material. This product is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific.

LUVOCOM®The main features of 1100-7721/WT9016 are:

- sterilizable
- Flame Retardant
- Good dimensional stability
- Typical application areas include:
- Electrical/electronic applications
- Reflector
- engineering/industrial accessories
- Aerospace
- Sporting goods

General Information			
Features	Good dimensional stability		
	Good disinfection		
	Disinfect with steam		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Reflector		
	Engineering accessories		
	Aerospace applications		
	Switch		
	Sporting goods		
	Medical/nursing supplies		
Appearance	White		
Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage	0.50 - 0.90	%	DIN 16901
Water Absorption (23°C, 24 hr)	< 0.10	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3000	MPa	ISO 527-2
Tensile Stress (Break)	85.0	MPa	ISO 527-2
Tensile Strain (Yield)	5.5	%	ISO 527-2
Flexural Modulus	2000	MPa	ISO 178
Flexural Stress	115	MPa	ISO 178
Coefficient of Friction			
Dynamic	0.34		

Static	0.28		
Flexural Strain at Flexural Strength	7.3	%	ISO 178
Maximum operating temperature-Short Term	220	°C	
Insulation Resistance	> 1.0E+12	ohms	IEC 60167
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	90	kJ/m <sup>2</sup>	ISO 179/1fU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	195	°C	ISO 75-2/A
Continuous Use Temperature	180	°C	UL 746B
Vicat Softening Temperature	215	°C	ISO 306/A
Injection	Nominal Value	Unit	
Drying Temperature - Desiccant Dryer	150	°C	
Drying Time - Desiccant Dryer	3.0 - 5.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	355 - 375	°C	
Middle Temperature	360 - 380	°C	
Front Temperature	350 - 370	°C	
Nozzle Temperature	340 - 360	°C	
Processing (Melt) Temp	350	°C	
Mold Temperature	120 - 200	°C	
Injection instructions			

#### General

In general LUVOCOM® can be processed on conventional injection moulding machines while observing the usual technical guidelines.

Any added fibrous materials or fillers may have an abrasive effect. In this case the cylinder and screw should be protected against wear as is usual in the processing of reinforced thermoplastic materials.

Lengthy dwell times for the melts in the cylinder should be avoided.

Lower the temperatures during interruptions!

Predrying (optional)

It is advisable to predry the granulate with a suitable dryer immediately before processing.

The granulate may absorb moisture from the air.

Delivery Form & Storage

Unless indicated otherwise, the material is delivered as 3mm-long pellets in sealed bags on pallets.

Preferably storage should be effected in dry and normally temperatured rooms

Additional Information

During processing the moisture level should not exceed 0.05%, otherwise porosity and surface defects (e.g. smearing) may occur. To avoid internal stresses, a low shear load should be used for processing. The parts may be tempered at a later stage to reduce internal stresses.

The processing notes provided merely represent a recommendation for general use. Due to the large variety of machines, geometries and volumes of parts, etc., it may be necessary to employ different settings according to the specific application.

High-temperature polymers place increased demands on the tool steels employed.

Please contact us for further information.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

