

Celanex® 2302 GV1/20

Polybutylene Terephthalate

Celanese Corporation

Message:

Chemical abbreviation according to ISO 1043-1: PBT
Moulding compound ISO 7792- PBT/PET, MGHR, 08-080N, GF20
Polybutylene terephthalate, polymer blend, 20 % glass fibre reinforced,
injection molded parts with superior gloss.
Flammability UL 94 HB minimum thickness 0.8 mm.
Recognition by Underwriters Laboratories, USA (UL)

General Information			
UL YellowCard	E42337-234689		
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Features	Highlight		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Multi-Point Data	Shear Modulus vs. Temperature (ISO 11403-1)		
Resin ID (ISO 1043)	PBT		
Physical	Nominal Value	Unit	Test Method
Density	1.47	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (265°C/2.16 kg)	19.0	cm ³ /10min	ISO 1133
Water Absorption (Equilibrium, 23°C, 50% RH)	0.15	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7800	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	135	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	%	ISO 527-2/1A/5
Flexural Stress (23°C)	175	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA
23°C	8.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	43	kJ/m ²	ISO 179/1eU
23°C	43	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	195	°C	ISO 75-2/A
8.0 MPa, not annealed	95.0	°C	ISO 75-2/C

Vicat Softening Temperature	220	°C	ISO 306/B50
Melting Temperature ¹	255	°C	ISO 11357-3
CLTE - Flow	3.5E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Dielectric Strength	29	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.40		IEC 60250
1 MHz	4.10		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	1.3E-3		IEC 60250
1 MHz	0.018		IEC 60250
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		UL 94
1.60 mm	HB		UL 94
Oxygen Index	20	%	ISO 4589-2
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	20.0 - 50.0	°C	
Rear Temperature	250 - 260	°C	
Middle Temperature	250 - 260	°C	
Front Temperature	260 - 270	°C	
Nozzle Temperature	265 - 275	°C	
Processing (Melt) Temp	265 - 275	°C	
Mold Temperature	90.0 - 100	°C	
Injection Pressure	60.0 - 100	MPa	
Injection Rate	Fast		
Holding Pressure	40.0 - 80.0	MPa	
Back Pressure	1.00 - 3.00	MPa	
Injection instructions			
Manifold Temperature: 265 to 275°CZone 4 Temperature: 260 to 270°CFeed Temperature: 190 to 200°C			
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

