

FLEXITEQ™ F67A010UV

Thermoplastic Vulcanizate

Marplex Australia Pty. Ltd.

Message:

FLEXITEQ™ F67A010UV is a formulation based on Santoprene™ rubber technology. It is formulated for extrusion including thin wall or complex profile applications in a pre-coloured material. FLEXITEQ™ F67A010UV is an improved UV resistant version and can be processed on conventional thermoplastic equipment for extrusion. It is polyolefin based and completely recyclable.

General Information			
Additive	UV stabilizer		
Features	Good UV resistance		
	Recyclable materials		
Uses	Thin wall parts		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.978	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	67		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	4.50	MPa	ASTM D412
Tensile Elongation ² (Break)	230	%	ASTM D412
Tear Strength ³ (23°C)	21.0	kN/m	ASTM D624
Compression Set ⁴			ASTM D395B
23°C, 70 hr	22	%	ASTM D395B
70°C, 22 hr	31	%	ASTM D395B
Extrusion	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 - 4.0	hr	
Cylinder Zone 1 Temp.	160 - 185	°C	
Cylinder Zone 3 Temp.	175 - 200	°C	
Cylinder Zone 5 Temp.	185 - 205	°C	
Melt Temperature	185 - 205	°C	
Die Temperature	185 - 205	°C	
Back Pressure	5.00 - 20.0	MPa	
Extrusion instructions			
Typical Mesh Screen Combination: 20/40/60			
NOTE			
1.	C mold, 500 mm/min		
2.	Mouth die C, 500 mm/min		
3.	C mold, 500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

