# MAJ'ECO BT160BS

## **Biodegradable Polymers**

AD majoris

## Message:

MAJ'ECO BT160BS is a biopolymer compound intended for injection moulding. MAJ'ECO BT160BS has been developed especially for demanding applications in various engineering sectors. APPLICATIONS Product such as: Boxes Racks Technical components

General Information			
Features	Updatable resources		
	Recyclable materials		
Uses	Bracket		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/10.0	20	(10) ·	100 1100
kg)	30	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	450	MPa	ISO 527-2/1
Tensile Stress (Break)	11.0	MPa	ISO 527-2/50
Flexural Modulus <sup>1</sup>	440	MPa	ISO 178
Flexural Stress	15.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	33	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Flammability	Nominal Value		Test Method
Flame Rating	НВ		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	4.0	hr	
Processing (Melt) Temp	160 - 190	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			

#### 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

