

# MAJORIS BG384

Polypropylene

AD majoris

## Message:

BG384 is a 30% chemically coupled glass fibre reinforced polypropylene compound intended for injection moulding and extrusion profiles .

The product is available in natural, but other colours can be provided on request.

BG384 has been developed especially for demanding applications in various engineering sectors.

BG384 has high rigidity and good impact strength, good dimensional stability and good creep resistancy also at high temperatures.

## APPLICATIONS

Product requiring very high overall mechanical performance such as:

Heater housing

Automotive under the bonnet components (brake fluid tank···)

Miscellaneous automotive technical items

Profiles

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Good dimensional stability		
	Rigidity, high		
	Chemical coupling		
	Impact resistance, good		
	Recyclable materials		
Uses	Good creep resistance		
	Parts under the hood of a car		
	Application in Automobile Field		
	Shell		
Appearance	Profile		
	Available colors		
Forms	Natural color		
	Particle		
Processing Method	Profile extrusion molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.0	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	0.60 - 0.90	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	65.0	MPa	ISO 527-2/50

Tensile Strain (Yield)	3.3	%	ISO 527-2/50
Flexural Modulus	4500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	13	kJ/m <sup>2</sup>	ISO 179/1eA
23°C	20	kJ/m <sup>2</sup>	ISO 179/1eA
Notched Izod Impact			ISO 180/1A
-20°C	16	kJ/m <sup>2</sup>	ISO 180/1A
23°C	21	kJ/m <sup>2</sup>	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	148	°C	ISO 75-2/B
1.8 MPa, not annealed	132	°C	ISO 75-2/A
Vicat Softening Temperature			
--	153	°C	ISO 306/A
--	122	°C	ISO 306/B
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	210 - 250	°C	
Mold Temperature	30.0 - 70.0	°C	
Injection Rate	Slow-Moderate		
Injection instructions			

Holding pressure: 50 to 70% of the injection pressure

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

