

VITAMIDE® BB3X

Polyamide 6
A. Schulman Europe

Message:

VITAMIDE® BB3X is a Polyamide 6 (Nylon 6) material filled with 50% glass bead. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of VITAMIDE® BB3X are:

Flame Rated
RoHS Compliant
Good Dimensional Stability
Heat Stabilizer

General Information			
Filler / Reinforcement	Glass Bead,50% Filler by Weight		
Additive	Heat Stabilizer		
Features	Good Dimensional Stability		
	Heat Stabilized		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cm³	ISO 1183
Molding Shrinkage	0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	90.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	4700	MPa	ISO 178
Flexural Stress	135	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	4.0	kJ/m²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	> 200	°C	ISO 75-2/B
1.8 MPa, Unannealed	130	°C	ISO 75-2/A
Melting Temperature (DSC)	221	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Comparative Tracking Index (Solution A)	525	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

