

Moplen EP540P

Polypropylene Impact Copolymer

LyondellBasell Industries

Message:

Moplen EP540P is a nucleated heterophasic copolymer, suitable for injection moulding applications.

It exhibits a high stiffness combined with a good impact balance.

Moplen EP540P is typically used in luggage, houseware items, containers, caps and closures.

Moplen EP540P is suitable for food contact.

General Information			
Additive	Nucleating Agent		
Features	Food Contact Acceptable		
	Good Impact Resistance		
	Good Stiffness		
	Impact Copolymer		
	Nucleated		
Uses	Caps		
	Closures		
	Containers		
	Household Goods		
	Luggage		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	20.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	63.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1400	MPa	ISO 527-2
Tensile Stress (Yield)	28.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	6.0	%	
Break	> 50	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-20°C	3.0	kJ/m ²	

0°C	3.5	kJ/m ²	
23°C	7.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-20°C	80	kJ/m ²	
0°C	120	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	90.0	°C	ISO 75-2/B
Ductile / Brittle Transition Temperature	-45.0	°C	ISO 6603-2
Vicat Softening Temperature			
--	151	°C	ISO 306/A50
--	68.0	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT