

Novalloy-S S3100V

Polycarbonate + ABS

PlastxWorld Inc.

Message:

Novalloy-S S3100V is a polycarbonate acrylonitrile butadiene styrene (PC ABS) product. It can be processed by injection molding and is available in North America. Novalloy-S S3100V applications include electrical/electronic applications, engineering/industrial accessories, tools, optics/lenses and agriculture. Features include:
flame retardant/rated flame
Flame Retardant
Good processability
anti-warping
Creep resistance

General Information			
Additive	Flame retardancy		
Features	Good dimensional stability		
	Bending resistance		
	Good formability		
	Good creep resistance		
	Good liquidity		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Electrical components		
	Power/other tools		
	Optical applications		
	Machine/mechanical parts		
	Agricultural application		
	Business equipment		
	Camera application		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (240°C/5.0 kg)	13	g/10 min	ISO 1133
Molding Shrinkage	0.40 - 0.60	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method

Tensile Stress (Yield)	51.0	MPa	ISO 527-2
Flexural Modulus	2300	MPa	ISO 178
Flexural Stress	81.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	40	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	114	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-0		UL 94
Additional Information			

The value listed as Mold Shrinkage, ISO 294, was tested in accordance with ISO 2577.

Injection	Nominal Value	Unit
Drying Temperature	87.8 - 110	°C
Drying Time	3.0 - 5.0	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	35 - 70	%
Rear Temperature	200 - 230	°C
Middle Temperature	220 - 240	°C
Front Temperature	230 - 250	°C
Nozzle Temperature	220 - 240	°C
Processing (Melt) Temp	241 - 260	°C
Mold Temperature	60.0 - 82.2	°C
Injection Pressure	48.3 - 96.5	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.345 - 1.38	MPa
Screw Speed	50 - 100	rpm
Clamp Tonnage	2.8 - 5.5	kN/cm ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT