

HIPOL™ J940

Polypropylene Impact Copolymer

Mitsui Chemicals, Inc.

Message:

HIPOL™ J940 is a Polypropylene Impact Copolymer (PP Impact Copolymer) material. It is available in Asia Pacific for injection molding.

Important attributes of HIPOL™ J940 are:

Flame Rated

Copolymer

Good Processability

Impact Resistant

Typical application of HIPOL™ J940: Engineering/Industrial Parts

| General Information | | | |
|---|------------------------|-------------------|-------------|
| Features | Block Copolymer | | |
| | Good Impact Resistance | | |
| | Good Moldability | | |
| Uses | Industrial Parts | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.910 | g/cm ³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 55 | g/10 min | ASTM D1238 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength (Yield) | 28.4 | MPa | ASTM D638 |
| Tensile Elongation (Break) | 50 | % | ASTM D638 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | | | ASTM D256 |
| -20°C | 20 | J/m | |
| 0°C | 39 | J/m | |
| 23°C | 64 | J/m | |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load | | | ASTM D648 |
| 0.45 MPa, Unannealed | 115 | °C | |
| 1.8 MPa, Unannealed | 55.0 | °C | |
| Vicat Softening Temperature | 150 | °C | ASTM D1525 |
| Flammability | Nominal Value | | Test Method |
| Flame Rating (1.57 mm, ALL) | HB | | UL 94 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT