SILPURAN® 8060/40

Silicone

Wacker Chemie AG

Message:

Silicone Rubber, HTV
Gaskets, Plastics and Rubber Processing
Membranes, Pharmaceuticals & Healthcare
Balloons, Pharmaceuticals & Healthcare
Catheters, Pharmaceuticals & Healthcare
Medical Tubing, Pharmaceuticals & Healthcare
Seals (HealthCare / Pharma), Pharmaceuticals & Healthcare
Valves (HealthCare / Pharma), Pharmaceuticals & Healthcare

| General Information | | | | | | | | | | |
|---------------------------------|--|-----------------|-------------|--|---|--|--|--|--|-------------|
| Features | Biocompatible | | | | | | | | | |
| | BPA Free Breathable | | | | | | | | | |
| | | | | | Good Chemical Resistance Good Flexibility Good Sterilizability Good Thermal Stability | | | | | |
| | High Gas Permeability High Heat Resistance | | | | | | | | | |
| | | | | | | | | | | High Purity |
| | Low to No Odor | | | | | | | | | |
| | Low to No Water Absorption | | | | | | | | | |
| | | Non-Toxic | | | | | | | | |
| | | Steam Resistant | | | | | | | | |
| | | | | | | | | | | |
| | Uses | Body Implants | | | | | | | | |
| | | Medical Devices | | | | | | | | |
| Medical/Healthcare Applications | | | | | | | | | | |
| Pharmaceuticals | | | | | | | | | | |
| | | | | | | | | | | |
| Agency Ratings | ISO 10993 | | | | | | | | | |
| | USP Class VI | | | | | | | | | |
| Processing Method | Compression Molding | | | | | | | | | |
| | Extrusion | | | | | | | | | |
| | Press Molding | | | | | | | | | |
| Heaving d Dunnantin | NamelantVel | Lla-it | TaskMatterd | | | | | | | |
| Uncured Properties | Nominal Value | Unit | Test Method | | | | | | | |

| Color | Clear/Transparent | | |
|-----------------------------|-------------------|-------|---------------|
| Density | 1.12 | g/cm³ | ISO 1183 |
| Cured Properties | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore A) | 40 | | DIN 53505 |
| Tensile Strength | 9.30 | MPa | DIN 53504 |
| Tensile Elongation at Break | 560 | % | DIN 53504 |
| Compression Set | 35 | % | DIN ISO 815-B |
| Tear Strength | 23.0 | kN/m | ASTM D624B |
| Rebound Resilience | 50 | % | DIN 53512 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

