

# PrimaFlex® RP 3501-C

Polypropylene Random Copolymer  
Plastic Solutions, Inc.

Message:

Description: RP 3501-C is a high melt flow random copolymer with fast cycle time and easy mold release. Its clarity makes it an excellent choice for "see-through" applications.

General Information			
Features	Fast Molding Cycle		
	Food Contact Acceptable		
	Good Mold Release		
	High Clarity		
	High Flow		
	Random Copolymer		
Uses	Containers		
	Vials		
Agency Ratings	FDA 21 CFR 177.1520		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	29.6	MPa	ASTM D638
Tensile Elongation (Yield)	13	%	ASTM D638
Flexural Modulus	1070	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	90.0	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

