

Andur 9-3 APLF

Polyurethane (Polyester, TDI)
Anderson Development Company

Message:

Andur 9-3 APLF is a polyester based liquid, toluene diisocyanate terminated prepolymer containing 0.1% or less free TDI monomer. An elastomer with a hardness of 92 to 94 Shore A is obtained when this prepolymer is cured with Curene 442 [4,4'-methylene-bis (orthochloroaniline)]. Elastomers of lower hardness can be obtained by reaction with various polyols and their combination with Curene 442, other diamines or through the use of plasticizers.

General Information			
Forms	Liquid		
Thermoset	Nominal Value	Unit	Test Method
Thermoset Mix Viscosity			ASTM D2393
70°C	1900	cP	ASTM D2393
100°C	450	cP	ASTM D2393
Additional Information			
NCO: 4.75%			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT