

# SILVER® SA-5304

Polyolefin

Guangdong Silver Age Sci & Tech. Co., Ltd

## Message:

SILVER® SA-5300 is low—smoke halogen-free flame retardant compound for cable which is polyolefin based material containing inorganic flame retardant, antioxidant,lubricant, etc. It is non-halogen, non-heavy metal, can pass RoHS. The series compound which can be radiation cross—linking makes it higher performance for temperature—resistant, better mechanical property and better insulating property. It can be used for power—cable, the cable for metro, and the cable for nuclear power plant, and so on.

Low Smoke Zero Halogen Flame Retardant Polyolefin Series

Thermoplastic Series

Characteristics:

low smoke zero halogen

Applications:

wire and cable, plug, electronic line and so on

General Information		
Additive	Antioxidant	
	Flame Retardant	
	Lubricant	
Features	Antioxidant	
	Flame Retardant	
	Halogen Free	
	Low Smoke Emission	
	Lubricated	
Uses	Electrical Parts	
	Electrical/Electronic Applications	
	Nuclear Power Applications	
	Plugs	
	Wire & Cable Applications	
RoHS Compliance	RoHS Compliant	
Physical	Nominal Value	Unit
Specific Gravity	1.50	g/cm³
pH	6.2	
Hot Pressure Test (80°C)	< 50	%
Halogenidric Acid Emissions	2.70	mg/g
Smoke Density		
Flame	59	
Non-flame	190	
Toxicity	0.800	
Electrical Conductivity	2.40	μS/mm

Hardness	Nominal Value	Unit
Durometer Hardness		
Shore A	88	
Shore D	40	
Mechanical	Nominal Value	Unit
Tensile Strength	9.80	MPa
Tensile Elongation (Break)	270	%
Aging	Nominal Value	Unit
Change in Tensile Strength (100°C, 168 hr)	21	%
Change in Ultimate Elongation (100°C, 168 hr)	-14	%
Electrical	Nominal Value	Unit
Volume Resistivity	8.0E+13	ohms·cm
Dielectric Strength	27	kV/mm
Flammability	Nominal Value	Unit
Oxygen Index	43	%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

