

# Generic Nylon 6 - Glass\Carbon Fiber

Polyamide 6

Generic

## Message:

This data represents typical values that have been calculated from all products classified as: Generic Nylon 6 - Glass\Carbon Fiber  
This information is provided for comparative purposes only.

General Information		
Filler / Reinforcement	Glass, carbon fiber reinforced materials	
Injection	Nominal Value	Unit
Drying Temperature	75.0 - 105	°C
Drying Time	3.0 - 13	hr
Processing (Melt) Temp	260 - 280	°C
Mold Temperature	60.0 - 100	°C
Injection instructions		

This data represents typical values that have been calculated from all products classified as: Generic Nylon 6 - Glass\Carbon FiberThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

