

# Plaslube® POM CO AF15

Acetal (POM) Copolymer  
Techmer Engineered Solutions

Message:

Plaslube® POM CO AF15 is an Acetal (POM) Copolymer product. It can be processed by injection molding and is available in North America. Characteristics include:  
Flame Rated  
Copolymer  
Lubricated  
Wear Resistant

General Information			
Additive	Aramid Resin Lubricant (15%)		
Features	Copolymer		
	Good Wear Resistance		
	Low Friction		
	Lubricated		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.80	%	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	107		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	88.3	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	4070	MPa	ASTM D790
Flexural Strength	116	MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.12		
vs. Steel - Static	0.070		
Wear Factor	26	10 <sup>-8</sup> mm <sup>3</sup> /N · m	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	80	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	160	°C	
1.8 MPa, Unannealed	154	°C	

CLTE - Flow	5.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength <sup>1</sup>	18	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	71.1	°C	
Drying Time	1.0	hr	
Rear Temperature	177 to 193	°C	
Middle Temperature	188 to 210	°C	
Front Temperature	182 to 199	°C	
Nozzle Temperature	177 to 204	°C	
Processing (Melt) Temp	193 to 216	°C	
Mold Temperature	82.2 to 121	°C	
NOTE			

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT