

Tarnamid® T- 29 MCS

Polyamide 6

Grupa Azoty S.A.

Message:

It is medium-high viscosity general purpose polyamide 6, containing release agent and colorant.

General Information				
Additive		Mold Release		
Features		Medium-high Viscosity		
Uses		Appliances		
		Automotive Applications		
		Electrical/Electronic Applications		
		Household Goods		
Appearance		Black		
		Green		
		Grey		
		Red		
		White		
		Yellow		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (275°C/5.0 kg)	50.0	--	cm ³ /10min	ISO 1133
Molding Shrinkage				ISO 294-4
Across Flow : 2.00 mm	1.8	--	%	
Flow : 2.00 mm	1.6	--	%	
Water Absorption				ISO 62
Saturation, 23°C	9.5	--	%	
Equilibrium, 23°C, 50% RH	3.0	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	150	75.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3200	1500	MPa	ISO 527-2/1
Tensile Stress (Yield)	82.0	45.0	MPa	ISO 527-2/50
Tensile Strain (Break)	30	100	%	ISO 527-2/50
Flexural Modulus ¹	2600	1100	MPa	ISO 178

Flexural Stress ²	85.0	30.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
--	5.0	13	kJ/m ²	
-30°C	3.0	--	kJ/m ²	
Notched Izod Impact Strength	4.5	13	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	60.0	50.0	°C	ISO 75-2/A
Vicat Softening Temperature	195	180	°C	ISO 306/B
Melting Temperature	221	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	9.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	1.2E-4	--	cm/cm/°C	
Limit of Temperature - a few hours operation	< 180	--	°C	
Temperature Index				
20000 hr	70	--	°C	
5000 hr	85	--	°C	
Burning Rate	+	--		FMVSS 302
ISO Type	PA6, MC2R, 18-030	--		ISO 1874
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+16	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+13	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	30	24	kV/mm	IEC 60243-1
Dielectric Constant (1 Hz)	3.50	4.20		IEC 60250
Dissipation Factor (1 Hz)	0.018	0.10		IEC 60250
Comparative Tracking Index (Solution A)	600	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (3.20 mm)	HB	--		UL 94
Glow Wire Flammability Index (2.00 mm)	650	--	°C	IEC 60695-2-12
Injection	Dry	Unit		
Drying Temperature	< 80.0		°C	
Suggested Max Moisture	< 0.10		%	
Suggested Max Regrind	50		%	
Processing (Melt) Temp	240 to 260		°C	
Mold Temperature	60.0 to 80.0		°C	
Injection Pressure	80.0 to 110		MPa	
Injection Rate	Fast			

NOTE

- | | |
|----|------------|
| 1. | 2.0 mm/min |
| 2. | 2.0 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

