

DENKA ABS SE-10

Acrylonitrile Butadiene Styrene

Denka Company Limited

Message:

DENKA ABS SE-10 is an Acrylonitrile Butadiene Styrene (ABS) product. It can be processed by extrusion and is available in Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

General Information			
UL YellowCard	E49895-241451		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.04	g/cm ³	ASTM D792
23°C	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	9.0	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	0.40 to 0.60	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	116		ASTM D785
R-Scale	108		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	47.0	MPa	ASTM D638
--	2400	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	49.0	MPa	
Break	35.0	MPa	
Nominal Tensile Strain at Break	26	%	ISO 527-2/50
Flexural Modulus			
-- ²	2450	MPa	ASTM D790
-- ³	2300	MPa	ISO 178
Flexural Strength			
-- ⁴	76.0	MPa	ASTM D790
-- ⁵	77.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	25	kJ/m ²	ISO 179
Notched Izod Impact	260	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed ⁶	91.0	°C	ASTM D648

1.8 MPa, Unannealed	80.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	102	°C	ASTM D1525 ⁷
--	103	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁸	> 1.0E+16	ohms	JIS K6911
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
NOTE			
1.	5.0 mm/min		
2.	15 mm/min		
3.	2.0 mm/min		
4.	15 mm/min		
5.	2.0 mm/min		
6.	Edgewise		
7.	Loading 2 (50 N)		
8.	23°C, 50% RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

