

YUPLENE® BX3800

Polypropylene Impact Copolymer

SK Global Chemical

Message:

YUPLENE BX3800 is a high crystalline propylene impact copolymer designed for injection molding applications. YUPLENE BX3800 has excellent properties in stiffness, flow, mechanical properties, heat resistance and impact strength, which make YUPLENE BX3800 suitable for auto parts, electric appliances, large size containers, thin wall and very high speed injection applications. This is not a chemical cracked grade so it is free from surface gas mark. YUPLENE BX3800 can reduce various injection problems such as surface trouble, shrink, warpage etc. and reduce the cycle time of injection molding due to rapid crystallization.

General Information			
Features	Crystalline		
	Good Impact Resistance		
	Good Stiffness		
	High Flow		
	High Heat Resistance		
Uses	Appliances		
	Automotive Applications		
	Containers		
	Electrical/Electronic Applications		
	Industrial Applications		
	Thin-walled Parts		
Processing Method			
Injection Molding			
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	30	g/10 min	ASTM D1238
Spiral Flow	> 80.0	cm	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	102		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	32.4	MPa	ASTM D638
Tensile Elongation (Break)	< 200	%	ASTM D638
Flexural Modulus	1860	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	49	J/m	
23°C	69	J/m	
Aging	Nominal Value	Unit	Test Method
Oven Aging	15.0	day	ASTM D3012
Heat Deflection Temperature	135	°C	ASTM D648

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	155	°C	ASTM D1525

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

