Thermoset Plastics 340 No.70

Epoxy; Epoxide

Thermoset, Lord Chemical Products

Message:

Thermoset Plastics 340 No.70 is an Epoxy; Epoxide (Epoxy) material filled with filler. It is available in North America for casting or encapsulating. Important attributes of Thermoset Plastics 340 No.70 are:

Conductive

Insulating

Low Viscosity

Typical application of Thermoset Plastics 340 No.70: Wire & Cable

General Information					
UL YellowCard	E84716-251618				
Filler / Reinforcement	Filler				
Features	Electrically Insulating				
	Low Viscosity				
	Thermally Conductive				
Uses	Electronic Insulation				
Appearance	Black				
Forms	Pellets				
Processing Method	Casting				
	Encapsulating				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	2.16	g/cm³	ASTM D792		
Water Absorption (24 hr)	0.17	%	ASTM D570		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore D)	90		ASTM D2240		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	64.8	МРа	ASTM D638		
Tensile Elongation (Yield)	4.1	%	ASTM D638		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact	26	J/m	ASTM D256		
Electrical	Nominal Value	Unit	Test Method		
Volume Resistivity	6.0E+15	ohms·cm	ASTM D257		
Dielectric Constant (1 MHz)	3.40		ASTM D150		
Dissipation Factor (1 MHz)	0.034		ASTM D150		
Thermoset	Nominal Value	Unit	Test Method		
Thermoset Components					
Hardener	Mix Ratio by Weight: 7.0				
Resin	Mix Ratio by Weight: 100				

Thermoset Mix Viscosity (25°C)	4000	сР	ASTM D2393
Demold Time (25°C)	1400	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

