

Petrothene® GA694189

Linear Low Density Polyethylene

LyondellBasell Industries

Message:

Petrothene GA694189 is a pelletized LLDPE copolymer resin selected by customers for injection molding. Typical applications include lids and thin-walled items that require high flow and short cycle times. GA694189 exhibits excellent flow, warp resistance and surface appearance.

General Information			
Features	Bending resistance		
	Fast molding cycle		
	High liquidity		
	Compliance of Food Exposure		
	Good appearance		
Uses	Thin wall parts		
Agency Ratings	FDA 21 CFR 175.1520		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.933	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	160	g/10 min	ASTM D1238
Spiral Flow	73.7	cm	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	62		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹			ASTM D638
Yield	17.2	MPa	ASTM D638
Fracture	15.9	MPa	ASTM D638
Tensile Elongation ² (Yield)	10	%	ASTM D638
Flexural Modulus ³			ASTM D790
1% secant	648	MPa	ASTM D790
2% secant	572	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	52.8	°C	ASTM D648
Brittleness Temperature	-7.22	°C	ASTM D746
Vicat Softening Temperature	92.2	°C	ASTM D1525
Injection	Nominal Value	Unit	
Rear Temperature	177	°C	
Middle Temperature	191	°C	

Front Temperature	204	°C
Nozzle Temperature	204	°C
NOTE		
1.	51 mm/min	
2.	51 mm/min	
3.	13 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT