

Duratuf™ 803U2/X

Acetal (POM) Copolymer

Technical Polymers, LLC

Message:

Duratuf™803U2/X is a polyoxymethylene (POM) copolymer material. This product is available in North America and is processed by extrusion or injection molding.

Duratuf™The main features of 803U2/X are:

- flame retardant/rated flame
- high viscosity
- UV stability

General Information	
Additive	UV stabilizer
Features	Viscosity, High
Forms	Particle
Processing Method	Extrusion Injection molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	58.6	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	50	%	ASTM D638
Flexural Modulus (23°C)	2410	MPa	ASTM D790
Flexural Strength (23°C)	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	154	°C	ASTM D648
1.8 MPa, not annealed	107	°C	ASTM D648
Melting Temperature	166	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

Additional Information		
Tensile Elongation, ASTM D638: >50%Volum Resistivity, ASTM D257: >1e13 ohm-cm		
Injection	Nominal Value	Unit
Drying Temperature	79.4	°C
Drying Time	2.0 - 4.0	hr
Processing (Melt) Temp	182 - 199	°C

Mold Temperature	65.6 - 98.9	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.103 - 0.345	MPa
Screw Speed	25 - 75	rpm
Clamp Tonnage	3.4 - 5.5	kN/cm ²
Cushion	3.18 - 12.7	mm
Screw L/D Ratio	20.0:1.0	
Screw Compression Ratio	2.5:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

