

PLASTRON™ PPS-CF40-01

Polyphenylene Sulfide

Daicel Polymer Ltd.

Message:

PLASTRON™ PPS-CF40-01 is a Polyphenylene Sulfide (PPS) material filled with 40% carbon fiber. It is available in Asia Pacific.

General Information			
Filler / Reinforcement	Carbon Fiber,40% Filler by Weight		
Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	190	MPa	ISO 527-2
Flexural Modulus	35000	MPa	ISO 178
Flexural Stress	370	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	20	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	285	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	120 to 140	°C	
Drying Time	3.0 to 5.0	hr	
Rear Temperature	300 to 320	°C	
Middle Temperature	310 to 330	°C	
Front Temperature	310 to 330	°C	
Nozzle Temperature	300 to 320	°C	
Mold Temperature	130 to 150	°C	
Back Pressure	5.00 to 10.0	MPa	
Screw Speed	40 to 60	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT