

RTP 300 TFE 10 SE A

Polycarbonate
RTP Company

Message:
Unreinforced - PTFE Lubricated - Self Extinguishing - Bromine/Chlorine Free - UL94 V-2

General Information			
UL YellowCard	E84658-251445		
Additive	PTFE lubricant (10%)		
Features	Chlorine Free		
	Lubrication		
	Bromine-free		
	Self-extinguishing		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.60 - 0.80	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Moisture Content	0.020	%	
Primary Additive	10	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2070	MPa	ASTM D638
Tensile Strength	53.8	MPa	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	2280	MPa	ASTM D790
Flexural Strength	86.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	210	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	No Break		ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	138	°C	ASTM D648
1.8 MPa, not annealed	135	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method

Flame Rating		UL 94
1.50 mm	HB	UL 94
3.00 mm	V-2	UL 94
Injection	Nominal Value	Unit
Drying Temperature	121	°C
Drying Time	4.0	hr
Dew Point	-28.9	°C
Processing (Melt) Temp	288 - 316	°C
Mold Temperature	82.2 - 121	°C
Injection Pressure	68.9 - 103	MPa
Injection instructions		

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

