Eleme NGL015FS

Linear Low Density Polyethylene

Eleme Petrochemical Company Ltd

Message:

NGL015FS is a Butene Co-monomer based Liner Low Density Polyethylene Resin manufactured by IEPL using "SCLAIRTECH" solution polymerisation process of DU Pont, Canada (Now Nova Chemicals) offers narrow molecular weight distribution copolymer with slip & antiblock additive which has been specifically designed for the production of high strength blown film of various thickness for multilayer & liners application.

General Information				
Additive	Anti-caking agent			
	slip agent			
Features	Low speed solidification crystal po	int		
	Butene comonomer			
	High strength			
	smoothness			
	Perforation resistance			
	Anti-caking property			
	Impact resistance, good			
	Good tear strength			
	Compliance of Food Exposure			
	Narrow molecular weight distribu	ion		
Uses	Blown Film			
	Packaging			
	Films			
	Lining			
	Multilayer film			
	Mixing			
Appearance	Natural color			
Processing Method	Film extrusion			
	Blow film			
	Co-extruded film			
Physical	Nominal Value	Unit	Test Method	
Specific Gravity	0.919	g/cm ³	ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/2.16		~		
kg)	1.5	g/10 min	ASTM D1238	
Films	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D882	

MD: Yield	12.0	MPa	ASTM D882
TD: Yield	11.5	MPa	ASTM D882
MD: Fracture	28.0	MPa	ASTM D882
TD: Fracture	25.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	700	%	ASTM D882
TD: Fracture	800	%	ASTM D882
TD: Fracture Additional Information	800 Nominal Value	% Unit	ASTM D882 Test Method
		-	
Additional Information	Nominal Value	Unit	Test Method
Additional Information Dart Impact	Nominal Value	Unit	Test Method ASTM D1709
Additional Information Dart Impact Tear Strength	Nominal Value 29.4	Unit kN/m	Test Method ASTM D1709 ASTM D1922

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

