

Kynar® 721

Polyvinylidene Fluoride

Arkema

Message:

KYNAR® 720 is a semi-crystalline low molecular weight pelletized polymer of vinylidene fluoride. It is a versatile engineering plastic with an outstanding balance of physical and chemical properties which qualify it for high performance service in a wide range of applications. It is a thermoplastic fluoropolymer capable of being fabricated in standard processing equipment. The molecular weight and molecular weight distribution have been carefully tailored to supply a grade suitable for a variety of processing requirements and end-use applications.

KYNAR® 720 is recommended for fine extrusion operations such as monofilament and thin, flat, and blown film. It is also suitable for injection molding applications where very thin cross-sections for intricate design require excellent melt flow characteristics. KYNAR® 720 is also suggested for coextrusion of composite constructions and as a base for filled or alloyed KYNAR® compounds.

The powder form of this resin grade is available as KYNAR® 721 PVDF.

General Information	
UL YellowCard	E54699-636461
Features	Low Molecular Weight
	Semi Crystalline
Uses	Blown Film
	Film
	Thin-walled Parts
Forms	Powder
Processing Method	Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.77 to 1.79	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR)	5.0 to 27	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	76 to 80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield, 23°C	44.8 to 55.2	MPa	
Break, 23°C	34.5 to 55.2	MPa	
Tensile Elongation (Break, 23°C)	20 to 100	%	ASTM D638
Flexural Modulus (23°C)	1380 to 2310	MPa	ASTM D790
Flexural Strength (23°C)	58.6 to 75.8	MPa	ASTM D790
Compressive Strength (23°C)	68.9 to 103	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	165 to 172	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method

Volume Resistivity ¹ (20°C)	2.0E+14	ohms·cm	ASTM D257
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (232°C, 100 sec ⁻¹)	600 to 1200	Pa·s	ASTM D3835
NOTE			
1.	65% R.H.		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

