

ISOTAL™ C13

Acetal (POM) Copolymer
SABIC Innovative Plastics Europe

Message:
General purpose, unfilled polyacetal (POM) copolymer resin.

General Information			
Features	Copolymer		
	General Purpose		
Uses	General Purpose		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	13	g/10 min	ISO 1133
Molding Shrinkage - Flow	2.1 to 2.9	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	114		ISO 2039-2
Ball Indentation Hardness (H 358/30)	140	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2800	MPa	ISO 527-2
Tensile Stress (Yield)	62.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	11	%	
Break	45	%	
Flexural Modulus	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength (23°C)	7.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	115	°C	ISO 75-2/A
Vicat Softening Temperature	150	°C	ISO 306/B120
Electrical	Nominal Value	Unit	Test Method
Electric Strength (in Air)	25	kV/mm	IEC 60243-1
Injection	Nominal Value	Unit	Test Method
Processing (Melt) Temp	185 to 200	°C	

Mold Temperature	75.0 to 95.0	°C
Injection Pressure	74.9	MPa
Injection Rate	Moderate	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

