

PENTALLOY BP GV30 H black

Polyamide 6 + PP
PENTAC Polymer GmbH

Message:
PA6+PP-alloy, 30% glass fiber reinforced, heat stabilised, resistant to corrosion

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Additive		heat stabilizer		
Features		Good corrosion resistance		
		Thermal Stability		
Agency Ratings		EC 1907/2006 (REACH)		
Appearance		Black		
Forms		Particle		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.26	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Transverse flow	0.80	--	%	ISO 294-4
Flow	0.40	--	%	ISO 294-4
Water Absorption				ISO 62
Saturated, 23°C	3.5	--	%	ISO 62
Equilibrium, 23°C, 50% RH	1.0	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9300	7200	MPa	ISO 527-2/1
Tensile Stress (Break)	130	97.0	MPa	ISO 527-2/5
Tensile Strain (Break)	2.4	3.9	%	ISO 527-2/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	8.0	--	kJ/m ²	ISO 179/1eA
23°C	10	11	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	45	--	kJ/m ²	ISO 179/1eU
23°C	55	53	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				

0.45 MPa, not annealed	210	--	°C	ISO 75-2/B
1.8 MPa, not annealed	195	--	°C	ISO 75-2/A
Melting Temperature	222	--	°C	ISO 11357-3
Flammability	Dry	Conditioned		Test Method
Flame Rating				UL 94
1.6 mm	HB	--		UL 94
3.2 mm	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	80		°C	
Drying Time	3.0		hr	
Suggested Max Moisture	0.050 - 0.13		%	
Suggested Max Regrind	20		%	
Rear Temperature	245 - 270		°C	
Middle Temperature	250 - 280		°C	
Front Temperature	250 - 270		°C	
Processing (Melt) Temp	240 - 280		°C	
Mold Temperature	40 - 80		°C	
Injection Pressure	50.0		MPa	
Screw L/D Ratio	18.0:1.0 to 22.0:1.0			
Screw Compression Ratio	2.2:1.0 to 2.8:1.0			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

