

HyTemp® AR12B

Acrylic

Zeon Chemicals L.P.

Message:

HYTEMP® POLYACRYLATE (ACM) elastomers are ideally suited for applications requiring long-term performance in severe temperature and fluid environments. HyTemp can be compounded to withstand an impressive temperature range from -40°C to 200°C. These elastomers offer excellent long-term heat and compression set resistance while providing superb resistance to petroleum and synthetic-based lubricants. HyTemp can be tailored to specific material specifications through the proper choice of elastomer grade. To accommodate multiple application needs, a wide range of HyTemp grades is available. Representing some of the industry's most advanced innovations, HyTemp yields exceptional compressive stress relaxation performance in high-temperature sealing functions. HyTemp can be processed using all common thermoset methods, including compression, transfer, injection molding, calendaring and extrusion. This makes HyTemp ideal for automotive under-hood applications such as transmission seals, engine seals, and both oil- and air-management hoses. Industrial applications include binders, adhesives and seals.

Special Properties/Applications

Faster curing version of AR12.

General Information	
---------------------	--

Features	High Heat Resistance
	Low Temperature Resistant
	Oil Resistant

Uses	Adhesives
	Automotive Under the Hood
	Binder
	Hose
	Industrial Applications
	Plastics Modification
	Seals

Physical	Nominal Value	Unit
----------	---------------	------

Specific Gravity	1.10	g/cm ³
------------------	------	-------------------

Mooney Viscosity	28 to 38	MU
------------------	----------	----

Additional Information	Nominal Value	Unit
------------------------	---------------	------

Cure Agent	Proprietary	
------------	-------------	--

Gehman Torsion Test - T100 ¹	-30	°C
---	-----	----

Volume Swelling ²	30	%
------------------------------	----	---

NOTE		
------	--	--

1.	On a nominal 65 Shore A, non-plasticized compound.	
----	--	--

2.	IRM 903 oil, 70 Hr. @ 150°C	
----	-----------------------------	--

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

