

VeroYellow RGD836

Unspecified

Stratasys

Message:

PolyJet rigid opaque materials give you brilliant color and includes VeroCyan™, VeroMagenta™, VeroYellow, VeroWhitePlus™, VeroGray™, VeroBlue™ and VeroBlackPlus™.

- Ideal for:
- Fit and form testing
 - Moving parts and assembled parts
 - Sales, marketing and exhibition models
 - Assembly of electronic components
 - Silicon molding

General Information			
Features	High Rigidity		
Uses	Electrical Parts		
	Engineering Parts		
	Modeling Material		
	Mold Making		
	Prototyping		
Appearance	Opaque		
	Yellow		
Processing Method	3D Printing, Jetted Photopolymer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17 to 1.18	g/cm ³	ASTM D792
Water Absorption (24 hr)	1.1 to 1.5	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	73 to 76		
Durometer Hardness (Shore D)	83 to 86		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000 to 3000	MPa	ASTM D638
Tensile Strength	50.0 to 65.0	MPa	ASTM D638
Tensile Elongation (Break)	10 to 25	%	ASTM D638
Flexural Modulus	2200 to 3200	MPa	ASTM D790
Flexural Strength	75.0 to 110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	20 to 30	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	45.0 to 50.0	°C	

1.8 MPa, Unannealed	45.0 to 50.0	°C	
Glass Transition Temperature	52.0 to 54.0	°C	DMA

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

