URE-BOND® II

Polyurethane

Smooth-On, Inc

Message:

URE-BOND® II is a premium performance urethane adhesive compound that offers a strong flexible bond between many different surfaces. URE-BOND® is ideal for adhering polyurethane rubber and other polymer products to many types of substrates (such as plaster, wood, cement, stone) and non-porous materials (such as glass, hard plastics and a variety of metals). URE-BOND® II has also been used to repair torn polyurethane molds on a limited basis (with proper surface preparation). Working time is 5 minutes at room temperature (73° F / 23° C). Once mixed and applied, URE-BOND® takes about 60 minutes to cure and yields a strong, flexible bond.

General Information			
Features	Bondability		
	Good Adhesion		
	Good Flexibility		
Uses	Adhesives		
	Bonding		
	Repairing Material		
Appearance	Amber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.10	g/cm³	ASTM D792
Specific Volume	0.903	cm³/g	
Handle Time (23°C)	1.0	hr	
Mixing Ratio	1A:1B by volume		
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4.83	МРа	ASTM D638
Tensile Strength (Break)	5.52	MPa	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	23.4	MPa	ASTM D412
Tensile Elongation (Break)	120	%	ASTM D412
Tear Strength ¹	30.6	kN/m	ASTM D624
Thermoset	Nominal Value	Unit	Test Method
Pot Life (23°C)	5.0	min	
Thermoset Mix Viscosity	5400	сР	ASTM D2393
Demold Time (23°C)	1400	min	
NOTE			
1.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

