

# Boda BDF-KK2702

Fluoroelastomer

Chenguang Fluoro & Silicone Elastomers Co., Ltd.

Message:

Material Type: Brown color fluoroelastomer compound, hardness Shore A 65-75.  
Based on bisphenol curable copolymers.  
Features: Excellent mold flow, improved tear resistance and bonding adhesion.  
Process Methods: Suitable for compression, transfer, extrusion and injection molding processes.  
Applications: oil seals, stem seals, crank shaft seals and complicated geometries.  
Lab Testing Curing Condition:  
Press Curing: 10min@170°C.  
Oven: (8+16)hrs@230°C

General Information			
Features	Bondability		
	Good Adhesion		
	Good Flow		
	Good Moldability		
	Good Tear Strength		
Uses	Seals		
Appearance	Brown		
Processing Method	Compression Molding		
	Extrusion		
	Injection Molding		
	Resin Transfer Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.01	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	72		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	14.5	MPa	ASTM D412
Tensile Elongation (Break)	260	%	ASTM D412
Compression Set <sup>1</sup> (200°C, 70 hr)	17	%	ASTM D395
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air (250°C, 70 hr)	-3.0	%	ASTM D573
Change in Ultimate Elongation in Air (250°C, 70 hr)	-8.0	%	ASTM D573
Change in Durometer Hardness in Air (250°C, 70 hr)	2.0		ASTM D573
Change in Tensile Strength (23°C, 70 hr, in Reference Fuel C)	-14	%	ASTM D471

Change in Ultimate Elongation (23°C, 70 hr, in Reference Fuel C)	-14	%	ASTM D471
Change in Durometer Hardness (23°C, 70 hr, in Reference Fuel C)	-2.0		ASTM D471
Change in Volume (23°C, 70 hr, in Reference Fuel C)	3.0	%	ASTM D471

#### NOTE

1. 6 mm Buttons

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT