

DOW™ Electrical & Telecommunications

DGDK-6924 NT EXP1

High Density Polyethylene Cellular Insulation Compound

The Dow Chemical Company

Message:

DGDK-6924 NT EXP1 is a high density polyethylene compound designed for use in physical foaming processes where high expansion rates (40 - 70%) are required. This compound is designed to offer excellent high speed processability as given by low extrusion pressures and smooth insulation surface quality. Furthermore, since it is fully pre-compounded with all the necessary ingredients, DGDK-6924 NT EXP1 offers better dispersion of the nucleating agent allowing high expansion rates to be achieved with more consistent processability (capacitance and diameter). It is stabilized for long term cable performance in data cable applications.

Applications:

Typical applications include LAN and data center cables.

Specifications

DGDK-6924 NT EXP1 should meet the following material specifications:

-

ASTM D 1248 Class A, Type III, Category 3

-

ISO 1875-PE, KGHN, 45-D-045

General Information			
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density ¹	0.952	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (140°C/5.0 kg)	5.5	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness ² (Shore D, 1 sec)	65		ISO 868
Thermal	Nominal Value	Unit	Test Method
Oxidation Induction Time (200°C)	> 50	min	ASTM D3895
Electrical	Nominal Value		Test Method
Dielectric Constant ³ (1 MHz)	2.30		IEC 60250
Dissipation Factor (50 Hz)	1.0E-4		IEC 60250
Cured Properties	Nominal Value	Unit	Test Method
Tensile Strength ⁴	21.0	MPa	IEC 60811-501
Tensile Elongation at Break ⁵	1400	%	IEC 60811-501
Extrusion	Nominal Value	Unit	
Melt Temperature	170 - 190	°C	

Extrusion instructions

DGDK- 6924 NT EXP1 can be processed using a range of commercial gas injection systems.It is normally extruded with a target melt temperature of 170 - 190 °C.Typical barrel temperatures required depend on extruder size and construction being made but a good starting point is:

Feed zone: 150 - 160 °C

Transition zone: 160 - 170 °C

Injection Point: 185 - 200 °C

Metering zone: 180 - 190 °C

Cross head and Die: 200 - 210 °C

NOTE

1.	On unannealed material from the melt flow rate extrudate
2.	Measured on compression moulded plaques
3.	Measured on compression moulded plaques
4.	Measured on extruded tape
5.	Measured on extruded tape

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

