LARIPUR® LPR 5925

Thermoplastic Polyurethane Elastomer (Polyester)

COIM S.p.A.

Message:

LARIPUR®LPR 5925 is a thermoplastic polyurethane elastomer (polyester) (TPU-polyester) material. This product is available in North America, Latin America or Europe. The processing method is injection molding.

LARIPUR® The main features of LPR 5925 are:

Good toughness Good tear strength good weather resistance chemical resistance

Wear-resistant

General Information							
Features	Low Temperature Flexibility						
	Good tear strength						
	Good wear resistance Good chemical resistance Good weather resistance						
					Good toughness		
Forms	Particle						
Processing Method	Injection molding						
Physical	Nominal Value	Unit	Test Method				
Specific Gravity	1.23	g/cm³	ASTM D792				
Hardness	Nominal Value	Unit	Test Method				
Durometer Hardness (Shore A)	59		ASTM D2240				
Mechanical	Nominal Value	Unit	Test Method				
Flexural Modulus	235	MPa	ASTM D790				
Elastomers	Nominal Value	Unit	Test Method				
Tensile Stress			ASTM D412				
50% strain	16.4	MPa	ASTM D412				
100% strain	18.7	MPa	ASTM D412				
300% strain	45.0	MPa	ASTM D412				
Tensile Strength (Break)	68.9	МРа	ASTM D412				
Tensile Elongation (Break)	390	%	ASTM D412				
Tear Strength	171	kN/m	ASTM D624				
		Unit	Test Method				
Thermal	Nominal Value	Unit	rest Metriod				

Abrasion loss, DIN 53516: 40 mm³Tosion Test, ASTM D 1043, 20° C: 58 MPaTosion Test, ASTM D 1043, -20° C: 370 MPaImpact Test, ASTM D 256, -20° C: 5.0 KJ/m²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

