

LAMIGAMID® 700

Ultra High Molecular Weight Polyethylene

Schwartz Technical Plastic

Message:

Applications:

Wear liners

Sliding Plates

General Information			
Uses	Lining		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ISO 1183
Water Absorption			ISO 62
23°C, 24 hr	0.0	%	ISO 62
Saturated, 23°C	> 0.10	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	57.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1100	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	39.0	MPa	ISO 527-2
Fracture	40.0	MPa	ISO 527-2
Tensile Strain (Break)	450	%	ISO 527-2
Flexural Modulus	790	MPa	ISO 178
Compressive Stress			ISO 604
20% strain	32.0	MPa	ISO 604
10% strain	25.0	MPa	ISO 604
5% strain	16.0	MPa	ISO 604
Coefficient of Friction			ASTM D1894
With steel-dynamic	0.020 - 0.080		ASTM D1894
With steel-static	0.29		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ISO 180
Unnotched Izod Impact Strength	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	136	°C	ISO 3146
CLTE - Flow (20 to 100°C)	2.0E-4	cm/cm/°C	ISO 11359-2
Specific Heat	2300	J/kg/°C	ASTM C351
Thermal Conductivity	0.33	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+14	ohms	IEC 60093
Dielectric Strength	100	kV/mm	IEC 60243-1
Dielectric Constant	2.30		IEC 60250
Dissipation Factor	1.0E-4		IEC 60250

Additional Information

Creep Rate Stress, DIN 53444, 1% Elongation: 3.2 N/mm² Creep Rate Stress, DIN 53444, 2% Elongation: 5 N/mm² Friction Wear: 1.0 μm/Km Coef of Friction, ASTM D1894, vs. Steel-Dynamic: 0.02 to 0.08 Penetration Resistance, DIN 53482: 1E17 ohm-cm Creepage/leakage Resistance: KA3c Thermal Expansion: 0.1 %/10°C Safe Temperature Range, short periods: 120°C Safe Temperature Range, permanent: -100° to 80°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT